

# PLANK 138 13 mm Clic

## Technical information:

<b>Produced according to:</b>	European parquet norm EN 13489 - 2014	
<b>Dimension:</b>	13 x 138 x 2200 mm	
<b>Toplayer:</b>	about 2.5 mm	
<b>Construction:</b>	3-layer construction; Hardwood toplayer, middlelayer and bottomlayer made of spruce Toplayer about 2.5 mm Middlelayer 8.8 mm Bottomlayer 1.9 mm	
<b>Boards/ m<sup>2</sup> per carton:</b>	10/ 3.04	
<b>Cartons/ m<sup>2</sup> per pallet:</b>	42/ 127.68	
<b>Slotted top layers per carton/ minimum length (mm):</b>	3/ 600	
<b>Weight per carton/ pallet in kg:</b>	24/ 1008	
<b>Floor heating systems:</b>	Well suitable to very well suitable	
<b>Fire behavior <sup>1)</sup>:</b>	Dfl-s1	
<b>Content of formaldehyd <sup>2)</sup>:</b>	E1	
<b>Content of pentachlorphenol (PCP) <sup>2)</sup>:</b>	not detectable	
<b>Density kg/ m<sup>3</sup> <sup>2)</sup>:</b>	about 550	
<b>Antislip performance:</b>	Live Satin	USRV 11 <sup>2)</sup>
	Live Matt	USRV 26 <sup>2)</sup>
	Live Natural	USRV 40 <sup>2)</sup>
<b>Abrasion resistance:</b>	Live Satin	70/ 1100 <sup>3)</sup>
	Live Satin	100 <sup>4)</sup>
<b>Thermal conductivity <sup>2)</sup>:</b>	0,15 W/ mK	
<b>Areal thermal resistance <sup>5)</sup>:</b>	0,093 m <sup>2</sup> K/ W	



DOP 4658-1.1-07.2015



Emissionsgeprüftes Bauprodukt nach DIBT-Grundsätzen.

1) nach DIN EN 13501-1, 2) nach DIN 14342, 3) nach ENV 13696, 4) nach DIN 68861, 5) nach EN 12524